



## Professional 625

### GENERAL DESCRIPTION

2-component, oil based and acid curing lacquer for use on wooden floors in high traffic commercial and residential areas.

Recommended as priming and finishing lacquer on untreated or sanded floors.

The lacquer is quick-drying and has a mild odour compared to similar products on the market.

Must be mixed with hardener before use.

For professional use only.

---

### PRODUCT DESCRIPTION

**Product:**

2-component, acid-curing lacquer with very high chemical resistance.

**Package sizes:**

5,2 liter (5 + 0,2 liter) in Matt and Silk matt.

**Appearance:**

Colourless film when dry.

---

**TECHNICAL DATA**

Coverage: 10 m<sup>2</sup> per litre.

Mixing: 25 parts of lacquer to 1 part of Hardener.

**Before application:** Stir/shake the lacquer thoroughly until any settled product has been stirred/shaken in. Pour hardener and stir/shake the lacquer thoroughly again, minimum 45 seconds. After adding hardener leave for 10 minutes. Stir/shake the lacquer again prior to use, minimum 45 seconds.

**Pot-life:**

24 hours at 20° C and 50 % RH.

**Application tools:**

Brush, mohair roller, air/airless spray. Don't apply by pouring out the lacquer directly on the floor.

**Substrate temperature:** Minimum 15° C.

**Dilution:** Delivered ready for use. Dilution is not recommended.

**Drying time at 20° C and 50 % RH :**

Recoating: 1½ hours.

Light traffic: 24 hours.

Fully cured after 3 days

**Cleaning of tools:** White spirit

**Storage:** Lasts for minimum 2 years if unopened and stored at 20° C.

---

**SYSTEM RECOMMENDATIONS****High and low traffic areas:**

1 coat Professional 625, gloss level Matt\* 10 m<sup>2</sup>/litre

+ 1 coat Professional 625 in wanted gloss level 10 m<sup>2</sup>/litre.

**Note \***

A more full-bodied finish is obtained when Professional 625 in Matt is used as primer.

---

## DIRECTION FOR USE

### Untreated/Sanded Floors:

Ensure that the surface is absolutely clean, dry and free from dust, wax, grease, polish etc. Sand the surface to remove dirt and irregularities. Vacuum thoroughly and wipe off with a well wrung cloth and clean water.

Prime with one coat of Professional 625 and allow drying.

Sand with sand paper grit 150-180 along the fibres of the wood. Vacuum sanding dust and wipe off with a well wrung cloth and clean water.

Apply one finishing coat of Professional 625.

### Previously sealed floors:

Machine sand by first using sandpapergrit 24-36 to strip old coats. Then remove abrasion marks using sand paper grit 60-80.

Finally, use sand paper grit 120-150 to obtain a completely smooth surface. Vacuum thoroughly and wipe off with a cloth well wrung in clean water.

Apply a coat of Professional 625 and allow drying.

Sand with fine sand paper (grit 150-180) along the fibres of the wood. Vacuum sanding dust and wipe off with a cloth well wrung in clean water.

Apply a further coat of Professional 625.

---

## PRECAUTIONARY MEASURES

Before use of the product, read the label on the container carefully and observe the advised precautionary measures.

See Material Safety Data Sheet for detailed information.

---